
Page 1 of 1	Hala Karasa Barahasa Carasa land	REV-01
Date: January 21, 2011	Holo-Krome Product Standard	HK.USA.DP.SPRL.BO



Pins, Pull Dowel, Spiral, Black Oxide, Manufactured in the USA

The information below lists the required dimensional, chemical and physical characteristics of the products in this purchase order. If the order received does not meet these requirements, it may result in a supplier corrective action request, which could jeopardize your status as an approved vendor. Unless otherwise specified, all referenced consensus standards must be adhered to in their entirety.



Nominal Size Thread Size	Thread Size	Α	D		P_L	Р	Т
		Max.	Max.	Min.	Min.	Max.	Min.
1/4	#8-32 UNC-2B	0.237	0.2503	0.2501	0.031	0.500	0.250
5/16	#10-32 UNF-2B	0.298	0.3128	0.3125	0.034	0.625	0.344
3/8	#10-32 UNF-2B	0.359	0.3753	0.3751	0.038	0.625	0.344
7/16	#10-32 UNF-2B	0.418	0.4378	0.4376	0.047	0.625	0.344
1/2	1/4-20 UNC-2B	0.480	0.5003	0.5001	0.047	0.750	0.375
5/8	1/4-20 UNC-2B	0.605	0.6253	0.6251	0.047	0.750	0.375
3/4	5/16-18 UNC-2B	0.725	0.7503	0.7501	0.059	0.875	0.375
1	3/8-16 UNC-2B	0.975	1.0003	1.0001	0.059	0.875	0.375

Specification Requirements:

• Dimensions: See dimensions above.

• Material &

Mechanical Properties: Hardenened ground machined carbon or alloy steel. Sulfur and

and Phosphorus content must not be in excess of 0.05 and 0.04 percent, respectively. Case hardness minimum 60 HRC, Case depth to be .020"

minimum. Core hardness of 47-58 HRC.

• Finish: Black Lustre